

RHEOLATE[®] 2001

Highly efficient anti-settling additives for highly pigmented aqueous systems

Key Benefits

- ❖ Outstanding anti-settling properties
- ❖ Easy to incorporate
- ❖ No elevated temperature for activation required

Introduction

RHEOLATE® 2001 is a highly efficient, pourable liquid, anti-settling additive dedicated for aqueous application.

RHEOLATE® 2001 has been based on a liquid dispersion of a proprietary aliphatic co-polymer containing functional carboxylate groups. These are in the delivery form of the product neutralized with an amine in order to make it compatible with water.

Typical applications of RHEOLATE® 2001 are Inks, paper coatings, pigment slurries and colorants as well as various kinds of water reducible applications.

Benefits and Features

- Outstandingly effective anti-settling properties
- Excellent syneresis reduction
- Minimum effect of low&mid shear viscosity
- Easy incorporation, no elevated temperature necessary
- Enhances spray application

Chemical and physical data

Composition	Olefinic copolymer colloidal suspension
Appearance	Translucent off-white liquid
Active content [%]	24
Solvent	water
Specific gravity [g/cm ³]	1.008

Mechanism and performance

The dispersed, colloidal copolymer particles are forming long chains in the rest, resembling strings of beads. Due to entanglement of the chain a three dimensional network is provided throughout the formulation. The resulting structure is open, however, supports finely divided pigments, extenders and fillers from sedimenting.

RHEOLATE® 2001 works best in highly filled systems. As it interacts with the solid material of the formulation building up a polymer network. As a consequence, the effectivity of RHEOLATE® 2001 is increasing with inclining filling grade.

In low solid system might not be enough particulate material to interact. In such cases, sedimentation might still occur, however, should be limited to soft settle. Problematic hard sedimentation is limited to a minimum.

RHEOLATE® 2001 provides long-term stability even in low viscous systems such as stains and wood care systems as well as industrial spray paints.

RHEOLATE® 2001 gives strong anti-settling performance and some sag control to a various water reducible systems and pigment dispersions. It only forms its network structure when the formulation is resting. This explains the minimum effect on the low and mid shear viscosity.

Further, RHEOLATE® 2001 does neither affect the gloss, the film build nor the levelling character of the final system.



Figure 1: Stability of aqueous ink

In Figure 1 is has been visualized that RHEOLATE® 2001 effectively eliminates settling and phase separation of a blue, aqueous ink system with a filling grade of 30%.

Incorporation

RHEOLATE® 2001 has been designed to be easy to incorporate. The low viscosity and the small particle size enables RHEOLATE® 2001 for the incorporation as a post-add additive. However, as it is shear stable addition millbase process is another suitable way of application.

In all cases, the proposed system needs to have a pH value of above 6.



NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2021, Elementis, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Registered trademark of Elementis, Inc.

North America

Elementis
469 Old Trenton Road
East Windsor,
NJ 08512, USA
Tel:+1 609 443 2500
Fax:+1 609 443 2422

Europe

Elementis UK Ltd.
c/o Elementis GmbH
Stolberger Strasse 370
50933 Cologne, Germany
Tel:+49 221 2923 2066
Fax:+49 221 2923 2011

Asia

Deuchem (Shanghai) Chemical Co., Ltd.
99, Lianyang Road
Songjiang Industrial Zone
Shanghai, China 201613
Tel:+86 21 5774 0348
Fax:+86 21 5774 3563